



Product Data Sheet

DuPont™ AmberLite™ FPA22 Ion Exchange Resins

Macroporous, Type II Strong Base Anion Resin for Mixed Bed Sweetener Applications

Description

DuPont™ AmberLite™ FPA22 Ion Exchange Resins are macroporous, Type II, strong base anion resins for use in mixed bed polishing in sweetener applications to produce syrup products with maximum shelf stability. The macroporous matrix provides excellent mechanical strength and good operating capacity.

AmberLite™ FPA22 OH Ion Exchange Resin is shipped in the regenerated (OH^-) ionic form.

AmberLite™ FPA22 Cl Ion Exchange Resin is shipped in the most stable (Cl^-) ionic form for long-duration shipments or inventory safety stock.

Anionic AmberLite™ FPA22 OH resin can best be used in a mixed bed polisher together with cationic AmberLite™ FPC88MB H Ion Exchange Resin. Or, for a pair of resins, each in their most stable form, AmberLite™ FPA22 Cl is commonly purchased with AmberLite™ FPC88MB Na Ion Exchange Resin, which is in the Na^+ form.

Applications

- Sweetener mixed bed polishing

Typical Properties

Physical Properties		
Copolymer	Styrene-divinylbenzene	
Matrix	Macroporous	
Type	Strong base anion, Type II	
Functional Group	Dimethylethanolamine	
Physical Form	White to yellow, opaque, spherical beads	
Chemical Properties		
Ionic Form as Shipped	OH ⁻	Cl ⁻
Total Exchange Capacity	≥ 1.2 eq/L (Cl ⁻ form)	≥ 1.2 eq/L
Water Retention Capacity	46 – 56% (Cl ⁻ form)	48 – 56%
Particle Size [§]		
< 300 μm	≤ 2%	≤ 1%
> 1180 μm	≤ 5%	≤ 2%
Stability		
Whole Beads	≥ 95%	≥ 95%
Swelling	Cl ⁻ → OH ⁻ : 12%	Cl ⁻ → OH ⁻ : 12%
Density		
Particle Density	1.1 g/mL	1.1 g/mL
Shipping Weight	670 g/L (42 lb/ft ³)	670 g/L (42 lb/ft ³)

[§] For additional particle size information, please refer to the [Particle Size Distribution Cross Reference Chart](#) (Form No. 45-D00954-en).

Suggested Operating Conditions

Maximum Operating Temperature (OH ⁻ form)	46°C (115°F)	
pH Range	0 – 14	
Bed Depth, min.	910 mm (3.0 ft)	
Flowrates		
Service	3 – 5 BV*/h	
Backwash	See Figure 1	
Fast Rinse (if applicable)	2 – 10 BV/h	
Contact Time		
Regeneration	≥ 30 – 45 minutes	
Displacement Rinse	≥ 30 – 45 minutes	
Total Rinse Requirement	3 – 6 BV	
Regenerant	NaOH †	Na ₂ CO ₃
Concentration	4%	7%
Level, 100% basis	64 – 80 kg/m ³ (4 – 5 lb/ft ³)	80 – 96 kg/m ³ (5 – 6 lb/ft ³)
Temperature, max.	46°C (115°F)	46°C (115°F)

* 1 BV (Bed Volume) = 1 m³ solution per m³ resin or 7.5 gal per ft³ resin

† NaOH is recommended.

Hydraulic Characteristics

Bed expansion of DuPont™ AmberLite™ FPA22 Ion Exchange Resin as a function of backwash flowrate at 25°C (77°F) is shown in Figure 1. The flowrate necessary to achieve a desired bed expansion for other water temperatures can be calculated with the provided equations.

Pressure drop data for AmberLite™ FPA22 as a function of service flowrate and viscosity is shown in Figure 2. These pressure drop expectations are valid at the start of the service run with clean feed.

Figure 1: Backwash Expansion

Temperature = 25°C (77°F)





Figure 2: Pressure Drop

Viscosity = 2 – 14 cP



For other temperatures use:

$$F_T = F_{25^\circ\text{C}} [1 + 0.008 (1.8T_C - 45)], \text{ where } F \equiv \text{m/h}$$

$$F_T = F_{77^\circ\text{F}} [1 + 0.008 (T_F - 77)], \text{ where } F \equiv \text{gpm/ft}^2$$

Product Stewardship

DuPont has a fundamental concern for all who make, distribute, and use its products, and for the environment in which we live. This concern is the basis for our product stewardship philosophy by which we assess the safety, health, and environmental information on our products and then take appropriate steps to protect employee and public health and our environment. The success of our product stewardship program rests with each and every individual involved with DuPont products—from the initial concept and research, to manufacture, use, sale, disposal, and recycle of each product.

Customer Notice

DuPont strongly encourages its customers to review both their manufacturing processes and their applications of DuPont products from the standpoint of human health and environmental quality to ensure that DuPont products are not used in ways for which they are not intended or tested. DuPont personnel are available to answer your questions and to provide reasonable technical support. DuPont product literature, including safety data sheets, should be consulted prior to use of DuPont products. Current safety data sheets are available from DuPont.

Please be aware of the following:

- **WARNING:** Oxidizing agents such as nitric acid attack organic ion exchange resins under certain conditions. This could lead to anything from slight resin degradation to a violent exothermic reaction (explosion). Before using strong oxidizing agents, consult sources knowledgeable in handling such materials.

Regulatory Note

This product may be used in applications that need to comply with relevant regulations. In support of these applications, a Regulatory Information Package is available upon request. Please address your request to your sales team or the contact details provided in this Product Data Sheet.

Have a question? Contact us at:

www.dupont.com/water/contact-us

All information set forth herein is for informational purposes only. This information is general information and may differ from that based on actual conditions. Customer is responsible for determining whether products and the information in this document are appropriate for Customer's use and for ensuring that Customer's workplace and disposal practices are in compliance with applicable laws and other government enactments. The product shown in this literature may not be available for sale and/or available in all geographies where DuPont is represented. The claims made may not have been approved for use in all countries. Please note that physical properties may vary depending on certain conditions and while operating conditions stated in this document are intended to lengthen product lifespan and/or improve product performance, it will ultimately depend on actual circumstances and is in no event a guarantee of achieving any specific results. DuPont assumes no obligation or liability for the information in this document. References to "DuPont" or the "Company" mean the DuPont legal entity selling the products to Customer unless otherwise expressly noted. NO WARRANTIES ARE GIVEN; ALL IMPLIED WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE ARE EXPRESSLY EXCLUDED. No freedom from infringement of any patent or trademark owned by DuPont or others is to be inferred.

© 2022 DuPont. DuPont™, the DuPont Oval Logo, and all trademarks and service marks denoted with ™, SM or ® are owned by affiliates of DuPont de Nemours Inc., unless otherwise noted.

